

BYK-326

Silicone-containing surface additive for solvent-borne, aqueous, and 100 % coatings with a slight reduction in surface tension and a slight increase in surface slip. Particularly suitable for good leveling.

Product Data

Composition

Polyether-modified polymethylalkylsiloxane

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.02 g/ml

Non-volatile matter: >96 %

Flash point: >100 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Coatings Industry

Special Features and Benefits

The additive causes only a slight reduction in the surface tension of the coating systems and has a positive effect on leveling. As a result of its broad compatibility, the high transparency of most clear coating systems is maintained and it can therefore be easily used in clear coatings for automotive, for example. In epoxy clear coatings for flooring, the additive combines high transparency, improved substrate wetting, and mild defoaming properties. Due to its special molecular structure, BYK-326 does not crystallize, even under -18 °C, which makes it easy to use at low temperatures.

Recommended Use

The additive is recommended for all solvent-borne, aqueous, and 100 % coatings.

Recommended Levels

0.05-0.5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Special Note

Unlike so-called silicone oils, this additive is very user-friendly. However, before use, one should determine in a test series whether foam is stabilized in certain systems. Similarly, the recoatability and cratering should be investigated.

BYK-326

Data Sheet
Issue 10/2018



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSORB®, RECYCLOSTAB®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® **are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany