

BYK-UV 3519

Nano-particle dispersion based on surface-treated silica for improving the scratch and abrasion resistance of solvent-free and solvent-borne radiation curable clearcoats.

Product Data

Composition

Dispersion of surface-treated silica nano-particles

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Nano-particle content:	40 %
Solvents:	Ethoxylated trimethylolpropane triacrylate
Non-volatile matter (20 min., 150 °C):	> 97 %
Particle size D_{50} :	20 nm
Viscosity (20 °C):	1100 mPa·s
Flash point:	81 °C
Density (20 °C):	1.38 g/ml

Storage and Transportation

To be stored and transported between 5 °C and 40 °C.

Special Note

The product must be stirred thoroughly before processing. Dried additive residues must be removed from the container since they can lead to seeds if introduced into the final product. Containers that are not completely emptied must be closed immediately after use as this may otherwise also lead to seeding.

Applications

Coatings Industry

Special Features and Benefits

This additive offers the highest level of scratch and abrasion resistance without negatively impacting properties such as gloss and transparency. It improves impact resistance and increases the flexibility of radiation curable clearcoats. The UV-reactive modification crosslinks the nano-particles with the binder. This further increases the hardness of the coatings. The combination of improved hardness and flexibility, particularly with UV hardcoats, enhances the selection of potential binders and monomers, even when they show strong shrinkage.

Recommended Use

The additive is recommended for solvent-borne and solvent-free radiation curable clearcoats which are used in general industrial coatings as well as in wood and furniture coatings.

Recommended Levels

1-25 % additive (as supplied) based on the total formulation.

In most cases, 1-5 % additive (as supplied) based on the total formulation is sufficient.
For a stronger effect, up to 50 % of nano-particles based on solid resin can be used.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The product reaches its full effectiveness when added at low shear. This ensures that even distribution in the binder system is achieved. It is recommended that all surface-active substances, such as silicones, are removed before laboratory testing. If required, leveling, substrate wetting, and surface slip can be optimized in a second step by using additives based on polyacrylate or silicone.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.