

Product Information

SITREN® MR 871

PRODUCT DESCRIPTION

SITREN® MR 871 is an emulsion concentrate based on biodegradable oils for the formulation of environmentally friendly mould release emulsions.

Typical Properties

Property	Unit	Value
Appearance		Milky white liquid
Density at 25°C	g/cm ³	0.94-0.97

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

- Concentrate for the formulation of stable mould release emulsions
- Mould release agent for on-site use in precast industry

Product Composition

Product Composition	Unit	Value
Active Content	wt%	54-58

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

SITREN® MR 871 reduces the adhesion between concrete and mould resulting in minimum cleaning efforts and wear of the mould.

At the same time surface properties/appearance of the concrete are improved.

Additionally, SITREN® MR 871 provides the following benefits and advantages.

- Excellent corrosion inhibition of metal moulds and heated moulds
- Smooth concrete surface
- Reduced number of pin holes and other defects of the concrete surface
- No discoloration of the concrete surface
- Reduced dust build-up on moulds resulting in a cleaner surface and less cleaning cycles
- For horizontal and vertical cast concrete applications
- Easy to dilute and to apply
- Dilutions of SITREN® MR 871 exhibit excellent storage stability (tap water may be suitable)
- Reduced health and environmental risks due to bio-degradable active material

DOSAGE

Typical coverage rates of SITREN® MR 871 (1:1 dilution) may vary from 10-18 ml/m².

For the formulation of stable mould release emulsions SITREN® MR 871 may be diluted 1:1 to 1:4 by adding water (demineralized water or soft tap water) to the concentrate. For non-metal moulds dilution ratios up to 1:9 with demineralized water are possible.

HANDLING & PROCESSING

The dilutions should be protected by adding a suitable preservative (e. g. Acticide MV, Acticide B20, THOR GmbH). For further information please contact us.

For direct use in precast applications SITREN® MR 871 has to be applied from predilutions. The mould should be thoroughly cleaned prior to application of the mould release agent. The entire mould surface has to be covered with

SITREN® MR 871, e. g. by spraying before placing the reinforcement. Any excess of the mould release agent needs to be removed in order to avoid adverse effects on the concrete surface properties.

In order to achieve the best release performance, the water from the release agent has to be let evaporated completely before the concrete is casted into the mould.

SITREN® MR 871 should not be applied at temperatures below 0 °C or during heavy rain falls.

PACKAGING

Pallet à 450 kg (9 x 50 kg can)

Container à 900 kg

SHELF LIFE

SITREN® MR 871 may be stored in closed containers for at least 6 months. The product has to be stored under frost-free conditions; storage temperature should not exceed 35°C.

The same applies to dilutions of SITREN® MR 871. Improper dilution conditions or preservation may adversely affect the stability of the diluted product.

HAZARDOUS SUBSTANCE

Information concerning

- Classification and labelling according to regulations for transport and for dangerous substances
- Protective measures for storage and handling
- Measures in case of accidents and fire
- Toxicity and ecological effects

is given in our material safety data sheets.

REGISTRATION LISTING SUMMARY

The relevant components of SITREN® MR 871 are listed/registered or exempt in the following chemical inventories.

Registration Listings	
Registry	Status
Australia (AIIC)	Information on Request
Canada (DSL)	Yes
China (IECSC)	Yes
EU (REACH)	Yes
EU (EINECS/ELINCS)	Yes
Japan (ENCS)	Yes
Taiwan (TCSI)	Yes
USA (TSCA)	Exempted
meets criteria for polymer exemption according to 40 CFR 723.750	

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Interface & Performance
Goldschmidtstraße 100
45127 Essen, Germany
Phone Europe +49 201 173-2665
Phone Asia +86 21 61191 125
Phone Americas +1 804 727 0700
interface-performance@evonik.com
evonik.click/interface-performance