Data Sheet Issue 10/2017

# **CERAFLOUR 970**

Micronized polypropylene-based wax for solvent-borne coating systems and powder coatings to improve anti-slip properties and for matting.

## **Product Data**

#### Composition

Micronized polypropylene wax

## **Typical Properties**

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density: 0.90 g/cm³ Melting point: 160 °C

Particle size distribution (laser diffraction, volume distribution): D50: 9 μm D90: 14 μm

Supplied as: Micropowder

## **Food Contact Legal Status**

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

## **Storage and Transportation**

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

# **Applications**

## **Powder Coatings**

## **Special Features and Benefits**

The additive reduces the gloss level and causes an anti-slip effect if higher dosages are used. The adhesion of sealers is improved as well as the protective effect of coatings against moisture.

#### **Recommended Use**

CERAFLOUR 970 is recommended for powder coatings based on polyester/TGIC/primid/powder link, polyester/epoxy, acrylate, polyurethane and epoxy.

## **Recommended Levels**

 $0.5-4\,\%$  additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## **Incorporation and Processing Instructions**

CERAFLOUR 970 should be mixed with resin, hardener, pigments and other additives using a high-speed mixer and extruded along with all components.

#### **CERAFLOUR 970**

Data Sheet Issue 10/2017

## **Liquid Coatings**

## **Special Features and Benefits**

The additive reduces the degree of gloss and causes an anti-slip effect in all solvent-borne coating systems.

#### **Recommended Levels**

0.5-5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## **Incorporation and Processing Instructions**

The additive is preferably incorporated into the coating at the end of the production process at a moderate shear rate.







**BYK-Chemie GmbH**P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com www.byk.com ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKOZBLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.