

# SCONA TPPP 9212 GA

Adhesion modifier to improve the mechanical properties of polypropylene filler and glass fiber compounds, polypropylene natural fiber compounds and one-packs in polypropylene.

## Product Data

### Composition

Polypropylene functionalized with maleic acid anhydride (MAH)

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

MFR (190 °C, 2.16 kg): 80-140 g/10 min

Drying loss (3 h, 110 °C): < 0.5 %

MAH content:  $\geq 1.8$  %

Supplied as: Granulate

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Storage temperature max. 35 °C, relative humidity < 80 %. Avoid direct sunlight and contact with water.

### Special Note

The modifier is also available as a powder under the name SCONA TPPP 9212 FA.

## Applications

### Thermoplastics

#### Special Features and Benefits

SCONA TPPP 9212 GA is a highly effective adhesion modifier for polypropylene compounds with short and long glass fibers and fillers (ATH,  $\text{Mg}(\text{OH})_2$ ,  $\text{CaCO}_3$ ) and polypropylene natural fiber compounds – even at a low dosage.

SCONA TPPP 9212 GA improves the mechanical properties of these compounds, especially in polypropylene natural fiber compounds. Here it also reduces water absorption.

In its supplied form (granulate), the modifier is highly suited to producing one-packs and masterbatches.

## Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation, depending on the fiber/filler content.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

Good wetting of the fibers/fillers is required for effective compounding. For this reason, the product must be added to the main feed.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany