

RHEOBYK-7670

Solid, non-dusting, biocide-, and VOC-free associative thickener (HEUR) for use in aqueous systems to increase the viscosity in the medium shear range.

Product data

Composition

Polyurethane

Biocide-free
VOC-free

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.20 g/cm³
Bulk density: 0.3–0.5 g/cm³
Active substance: 100 %
Melting point: 58 °C
Color: off-white
Delivery form: flakes

Storage and transportation

Storage at max. 35 °C.

Applications

Coatings industry

Special features and benefits

RHEOBYK-7670 increases viscosity in the medium shear range with a low impact in the high shear range. Using the additive optimizes workability properties and results in an excellent balance between the flowability and leveling. RHEOBYK-7670 has no negative effect on gloss or color acceptance.

The additive is supplied as flakes, is non-dusting, and is safe to handle. The solid delivery form means there is no need to add biocides to the additive to prevent microbial infestation.

It is not necessary to specifically adjust the pH value or control the temperature during incorporation.

Recommended use

RHEOBYK-7670 is preferably used in emulsion paints and coatings that are based on acrylate, styrene acrylate, and polyvinyl acetate binders, as well as in PU and alkyd emulsions and epoxy dispersions.

Architectural coatings	■
Wood and furniture coatings	■
Industrial coatings	■
Marine and protective coatings	■
Floor coatings	■

■ especially recommended □ recommended

Recommended levels

0.1–0.5 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

Incorporation while stirring ensures optimum distribution and the best possible effectiveness and reproducibility in applications. RHEOBYK-7670 is perfectly suitable for adding to the millbase and improving dispersibility. It can also be used as a post-additive. This requires a slightly longer incorporation time (no high shear forces) compared with conventional liquid polyurethane thickeners. Furthermore, a 10 % pregel solution is easy to produce and enables an optimized post-addition.

When used in clearcoats, it is recommended that the additive is stirred into water at the start of the manufacturing process, and that further formulation components, such as binders, etc., are then added while stirring.

Adhesives and sealants**Special features and benefits**

RHEOBYK-7670 increases viscosity in the medium shear range with a low impact in the high shear range. This optimizes the storage stability. Using RHEOBYK-7670 improves workability properties and results in an excellent balance between flowability and leveling.

The additive is supplied as flakes, is non-dusting, and is safe to handle. The solid delivery form means there is no need to add biocides to the additive to prevent microbial infestation.

It is not necessary to specifically adjust the pH value or control the temperature during incorporation.

Recommended use

RHEOBYK-7670 is suitable for use in highly polar and aqueous binder systems.

Recommended levels

0.1–0.6 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

Incorporation while stirring ensures optimum distribution and the best possible effectiveness and reproducibility in applications. RHEOBYK-7670 can also be used as a post-additive. This requires a slightly longer incorporation time (no high shear forces) compared with conventional liquid polyurethane thickeners. Furthermore, a 10 % pregel solution is easy to produce and enables an optimized post-addition.

**BYK-Chemie GmbH**

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK®-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.