

Product information

VESTAGON® B 1530

CROSSLINKING AGENT FOR POLYURETHANE POWDER COATINGS

GENERAL DESCRIPTION

VESTAGON B 1530 is a polyisocyanate adduct used in combination with hydroxy functional resins. Due to the e-Caprolactam blocked NCO-groups it is stable during processing up to the unblocking temperature of more than 160 °C. The crosslinker is delivered in the form of pellets.

SPECIFICATION

Property	Value	Unit	Test method
NCO content (total)	14.8 - 15.7	% wt	according to DIN EN ISO 11 909
NCO content (free)	≤ 1	% wt	DIN EN ISO 11 909
Glass transition temperature	41 - 53	°C	DSC

TYPICAL PROPERTIES

Property	Value	Unit	Test method
NCO-equivalent	~ 275	g/Eq	-
Density	1.14	g/cm ³	DIN 53 479
Bulk density	~ 670	kg/m ³	DIN 53 466
Melting range	62 - 82	°C	DIN 53 736
Flashpoint	~ 195	°C	ISO 2592
Ignition temperature	440	°C	DIN 51 794

APPLICATIONS

Numerous OH-terminated polyester and acrylics can be used to achieve weather-resistant decorative powder coatings with excellent physical properties. These polyols have a determining influence on the performance of the coating.

FORMULATIONS

Crosslinker and polyester are used in equivalent amounts. Empirically determined “under indexing” (up to NCO:OH = 0.8 : 1) yields economical coatings which exhibit excellent physical properties meeting the required performance profile.

EXAMPLES OF FORMULATION FOR BINDER COMBINATIONS

Crosslinking ratio (NCO:OH)	1 : 1		0.8 : 1		
VESTAGON B 1530	13	20	11	17	parts
Polyol (OH number 30)	87	-	89	-	parts
Polyol (OH number 50)	-	80	-	83	parts

Up to 1 % by weight degasser is often used in pigmented powder coatings to minimize surface imperfections.

CURING

The curing temperature for PUR powder coatings based on VESTAGON B 1530 lies above the splitting temperature of about 160 °C. A prerequisite for good physical properties of a coating is sufficient curing in the range of 180 °C 20 minutes up to 200 °C 10 minutes total oven time, according to the following standard procedures.

- Premixing: MTI-Mixer 2' - 500 rpm
- Extrusion: W&P ZSK 30 90 °C - 250 rpm
- Application: Manual spray gun 80 kV; steel panels 0.8 mm
- Curing: Air-circulated Heraeus oven; coating thickness 55-75 µm

APPLICATIONS FOR POLYURETHANE POWDER COATINGS

PUR powder coatings have been successfully used for many years in both exterior and interior applications such as:

- motor vehicle parts
- fittings
- bicycle frames
- fork lift trucks
- exterior furniture and lawn equipment
- agricultural machinery
- appliances
- telephone booths

STORAGE AND PACKAGING

The product is delivered in flat bags, net weight 25 kg. If kept cool (0 – 40 °C) and dry in closed bags the product can be stored for at least 1 year in accordance to the specification. All opened bags should be carefully resealed immediately after use.

SAFETY AND HANDLING

Please refer to our Safety Data Sheet.

Marl, January 26, 2022; This data sheet replaces all former issues.

VESTAGON® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH
Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers
For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION
Business Line Crosslinkers
299 Jefferson Road,
Parsippany, NJ 07054-0677
USA

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.
Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

