

Technical Information

GORAPUR® LK 8901-11-3 B**Description**

Gorapur® LK 8901-11-3 B is a solvent based release agent for the manufacturing of cold cured cushion foam.

Key performance benefits

- Easy Release.
- Low build-up in the moulds.
- Low spraying amounts.
- Suitable for use with electrostatic sprayguns.
- Excellent surface finish.

Typical properties*

Appearance	White dispersion
Density at 25 °C	0,75–0,79 g/cm ³
Carrier	Isoparaffines
Flashpoint	55–60 °C

* For actual ranges, please refer to the Certificate of Analysis (CoA) / Sales Specification.

Application

- Preferred mould temperature: 50–75 °C
- Demoulding of cold cured flexible foam for automotive seats and furniture. MDI, MDI/TDI and TDI systems.

Instruction for use

The product is a ready-to-use release agent. The concentration of waxes is much higher in this product than in conventional release agents.

High solids must be sprayed very carefully in order to create a thin layer with uniform distribution. A thicker layer of release agent will not enhance the release effect but will tend to impede it instead.

For the application of high solids, we recommend air-spray devices with two separate pressure adjustments: one for atomisation with the pistol and one for pressure on the material (pressure pot or membrane pump). Airless spraying equipment can also be used where higher outputs are required.

A set distance should be maintained between the gun and mould surface in order to optimise film formation. In case of a very short cycle time or very low mould temperatures, we recommend blowing air onto the film or wiping it with cloth after spraying.

Device adjustment

Spray gun	Air-mix or air-spray, e. g., W 3 FZ, duo or any other air assisted equipment
Nozzle	0,3–0,5 mm Ø
Pressure on material	Approx. 0,5 – 2,5 bar
Pressure on air	Approx. 1,0 – 2,5 bar

Preliminary tests are recommended.

Storage recommendations

- Stir well prior to use!
- Keep away from sources of ignition and ensure good ventilation.
- Do not store outside.
- Storage temperature: 10 to 30 °C.
- Shelf life from the date of manufacture: 12 months. For exact date of expiration, please consider CoA.

Safety instructions

Please consult the Safety Data Sheet for summary of product hazards, personal protective measures, and emergency release procedures.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Evonik Operations GmbH
Rellinghauser Straße 1-11
45127 Essen, Germany
Phone: +49 201 173 3006
Email: polyurethane@evonik.com



For any further information, contact either your regional sales or technical support or visit our customer portal explorepu.evonik.com.