

AQUACER 8059

Emulsion based on a HD polyethylene wax for improving the surface properties of aqueous care products and polishes as well as in aqueous coatings and printing inks.

AQUACER 8059 is only available in USA, Mexico and Canada.

Product Data

Composition

APEO-free, non-ionic emulsion of an oxidized high density polyethylene wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (ASTM D2834): 35 %
Carrier: Water
Melting point (wax component): 140 °C (284 °F)
Viscosity (25 °C, Brookfield DV-I): < 150 mPa·s
pH value (ASTM E70): 9

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Keep from freezing. To be stored and transported at a temperature between 5 °C (41 °F) and 35 °C (95 °F).

Applications

Care Products and Polishes

Special Features and Benefits

AQUACER 8059 improves the buffability, and black heel mark resistance. The above mentioned properties are generated by mixing AQUACER 8059 with polymers in a ratio of 3:1 (solid wax to solid polymer). A mixing ratio of 1:6 increases the water- and alcohol-resistance, the protection against heel marks (= foot traffic resistance), and the dirt-repellent action. AQUACER 8059 is compatible with all known polymer dispersions and plasticizers.

Recommended Use

AQUACER 8059 is recommended for self-shine emulsions and polishes.

Recommended Levels

5-10 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The wax additive is preferably added under agitation after mixing the polymers with the plasticizers and water, but before incorporating surface-active substances. Stir well before use.

Coatings and Printing Inks

Special Features and Benefits

The additive improves the scratch resistance in aqueous coatings. It increases the abrasion resistance in printing inks, as well as the resistance to black heel marking in parquet coatings.

Recommended Use

Aqueous coatings and printing inks.

Recommended Levels

1-6 % additive (as supplied) based upon total formulation for coatings.

3-14 % additive (as supplied) based upon total formulation for printing inks.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporating and Processing Instructions

The additive should preferably be post-added using low speed agitation. Stir well before use.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA