

## CERAFLOUR 1002

Biodegradable, micronized polymer with wax-like properties based on renewable raw materials for aqueous, solvent-borne, solvent-free, and UV systems for matting and improving surface protection while maintaining high transparency. Creates a soft feel effect and a slightly textured surface.

### Product Data

#### Composition

Micronized, modified biopolymer

VOC-free (< 1500 ppm)  
BRC content: > 97 %

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

|   |                        |
|---|------------------------|
| Density (20 °C):  | 1.25 g/cm <sup>3</sup> |
| Melting point:  | 175 °C                 |
| Particle size distribution<br>(laser diffraction, volume distribution):   | D50: 6 µm, D90: 31 µm  |
| Supplied as:  | Micropowder            |
| Proportion of biorenewable carbon (BRC)<br>in the total organic carbon content<br>(ASTM D6866-20 method B (AMS)): | > 97 %                 |

#### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C. CERAFLOUR 1002 is readily biodegradable and is therefore sensitive to microbial infestation if stored in open containers in a damp environment.

### Applications





#### Coatings Industry

##### Special Features and Benefits

CERAFLOUR 1002 enhances scratch resistance and creates a soft feel effect. The additive has a matting effect, especially in radiation curable systems, and produces very transparent coatings. CERAFLOUR 1002 facilitates the creation of a slightly textured surface thanks to its particle size distribution. It has no effect on the viscosity and surface slip, and does not cause foam stabilization. CERAFLOUR 1002 is readily biodegradable and is composed of > 97 % renewable raw materials.

**Recommended Use**

The additive is recommended for aqueous, solvent-borne, solvent-free, and UV systems.

|                             |   |
|-----------------------------|---|
| Wood and furniture coatings |  |
| General industrial coatings |  |
| Floor coatings              |  |
| Architectural coatings      |  |

 especially recommended    recommended

**Recommended Levels**

1-10 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

The additive should preferably be post-added to the coating using a low shear rate. Aqueous slurries of CERAFLOUR 1002 that will not be processed immediately must have a suitable preservative added so as to protect against microbial infestation.

**Printing Inks****Special Features and Benefits**

CERAFLOUR 1002 reduces the gloss value of aqueous and solvent-borne printing inks, overprint varnishes, and radiation curable systems, while simultaneously ensuring high transparency. The additive provides an excellent soft feel effect and can also provide anti-slip properties when used in high doses.

**Recommended Levels**

1-5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

The additive should preferably be incorporated into the printing ink or overprint varnish at a medium shear rate at the end of the production process.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFLOUR®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.