

## BYK-A 500

Silicone-free air release additive for unsaturated polyester resins as well as polyurethane and epoxy systems; particularly recommended for transparent systems. Also suitable for epoxy floorings.

### Product Data

#### Composition

Solution of polyolefin

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.88 g/ml
Refractive index (20 °C):	1.495
Flash point:	45 °C
Hazen color number:	< 200
Turbidity:	< 10 TE/F

### Applications

#### Ambient Curing Systems

##### Special Features and Benefits

BYK-A 500 is a highly effective air release additive for virtually all unsaturated polyester resins and processing techniques as well as for epoxy and polyurethane resins. Due to its compatibility, the air release additive is also particularly recommended for transparent systems.

##### Recommended Use

Particularly recommended for unsaturated polyester resins, gel coats and casting systems as well as for epoxy floorings and polyurethane systems.

##### Recommended Levels

0.1-0.5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

##### Incorporation and Processing Instructions

Stir in the resin before adding other components. In some resins, air release additives may cause haze in the finished part.

## BYK-A 500

Data Sheet  
Issue 08/2021



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.