

BYKJET-9151

Wetting and dispersing additive for solvent-borne, aqueous and UV-curing inkjet inks.

Product data

Composition

Styrene-maleic anhydride copolymer

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	1.10 g/ml
Non-volatile matter (30 min, 150 °C):	> 98,5 %
Flash point:	> 150 °C
Acid value:	8 mg KOH/g
Amine value:	18 mg KOH/g

Applications

Inkjet inks

Special features and benefits

The additive enhances pigment wetting and improves optical properties (color strength, gloss, haze and transparency) because of its outstanding pigment stabilization. It not only reduces the level of viscosity in pigment concentrates and final inkjet inks, but also prevents thixotropy. The additive can achieve long-term storage stability without a viscosity shift. It provides equal electrical charge to the pigment particles, and thus prevents possible co-flocculation of particles that are not equally charged. Excellent pigment deflocculation leads to small particle size and narrow particle size distribution, thereby significantly reducing filtration time. BYKJET-9151 may be used in all types of aqueous, solvent-borne and UV-curing inkjet inks. It can stabilize most pigments commonly used in inkjet inks.

Recommended use

Aqueous inkjet inks	■
Solvent-borne inkjet inks	■
UV-curing inkjet inks	■

■ especially recommended □ recommended

Recommended levels

Additive (as supplied) based on:

Organic pigments: 20–60 %

Carbon black: 30–100 %

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

Wetting and dispersing additives should be added to the millbase. This way, they can achieve their full effectiveness. Binder and solvents/water/reactive diluents are premixed with the additive while stirring, and should be homogenized before the pigment is added.



**Your local
contact**

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.