

BYK-070

Silicone and polymer defoamer/air release agent for adhesives and sealants as well as ambient curing acrylic systems.

Product Data

Composition

Solution of foam-destroying polymers and polysiloxanes

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.89 g/ml
Non-volatile matter (10 min., 150 °C):	9 %
Solvents:	Xylene/Methoxypropyl acetate/Butyl acetate 10/2/1
Flash point:	25 °C

Applications

Adhesives & Sealants

Special Features and Benefits

Prevents foam and bubble formation during manufacturing and application.

Recommended Use

Especially recommended for systems on acrylic resin basis.

Recommended Levels

0.3-1 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Incorporate into resin before adding the other components.

Ambient Curing Systems

Special Features and Benefits

Prevents foam and bubble formation during manufacturing and application.

Recommended Use

Recommended for ambient curing acrylic resins (syrup).

Recommended Levels

0.5-1 % additive (as supplied) based upon syrup.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Incorporate into resin before adding the other components.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany