

BYK-1810

PFAS-free, silicone-containing defoamer for solvent-borne and solvent-free coating systems, adhesives and sealants, and thermosets.

Product data

Composition

Solution of polysiloxanes

PFAS-free

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.88 g/ml
Non-volatile matter (10 min, 150 °C):	0.9 %
Solvents:	Butyl acetate
Flash point:	26 °C

Applications

Coatings industry

Special features and benefits

BYK-1810 is a highly effective defoamer for solvent-borne and solvent-free coating systems. Even at low dosing levels, optimal and spontaneous defoaming can be achieved.

Recommended use

Architectural coatings	■
Floor coatings	■
Marine coatings	■
Protective coatings	■
General industrial coatings	■
Automotive refinish coatings	□

■ especially recommended □ recommended

Recommended levels

0.1–1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated later, sufficient shear forces must be applied to ensure a good defoamer distribution and to prevent crater formation.

Adhesives and sealants

Special features and benefits

BYK-1810 is a highly effective defoamer for solvent-borne and solvent-free adhesive systems. It is particularly recommended for systems based on polyurethane and epoxy resins, in which it achieves optimal defoaming and good compatibility.

Recommended levels

0.1–1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

In order to achieve optimal defoaming, the defoamer should be incorporated into the resin with adequate shear forces before adding other components. You can also add the product to finished systems.

Thermosets

Special features and benefits

BYK-1810 is a highly effective air release agent, which reduces the formation of foam during the manufacture and processing of epoxy resin and polyurethane systems to obtain blister-free surfaces.

Recommended use

This additive is especially recommended for casting systems (polymer concrete formulation, electrical castings) based on epoxy resin and polyurethane.

Recommended levels

0.1–0.7 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

The additive is stirred into the resin before adding other components. You can also add the product to finished systems.



Your local
contact

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.