LAPONITE-XLS XR

Rheology additive based on synthetic phyllosilicate for aqueous systems to provide thixotropic stabilization in personal care applications.

Gamma irradiation sterilized version of LAPONITE-XLS.

Product data

Composition
Synthetic (modified) phyllosilicate
(INCI: Lithium Magnesium Sodium Silicate (nano), Tetrasodium Pyrophosphate)

Vegan

Typical properties
The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density:	1000 kg/m³
pH value (2 % in H_2O):	approx. 10
Moisture content:	max. 10 %
Sieve residue (60 mesh/250 µm):	max. 2 %
Surface area:	330 m²/g
Sol stability (24 h), as sol:	max. 50 cP
Dispersion rate:	max. 30
Clarity:	max. 20
Lead content:	max. 5 mg/kg
Arsenic content:	max. 1 mg/kg
Total viable count:	max. 10 cfu/g
Color:	white
Delivery form:	free-flowing powder

Storage and transportation
LAPONITE-XLS XR is hygroscopic and should be transported and stored dry in the unopened original container at temperatures between 0 °C and 30 °C.

Applications

Personal care

Special features and benefits
LAPONITE-XLS XR is suitable for use in formulations with a pH value of 6.5 and lower. In water or aqueous solutions of alcohols, it swells to produce clear and colorless colloidal dispersions of low viscosity known as sols. At additive concentrations of 10 % in water, these remain free-flowing for up to 24 hours. The additive is also suitable for use in hard water, since the inorganic phosphate is an effective sequestrant for Ca^{2+} and Mg^{2+} ions. The unique thixotropic formulations provided by LAPONITE-XLS XR improve the skin feel of personal care products and create a light, non-sticky texture. In addition, the additive enhances the stability of emulsions and prevents the settling of particles, pigments, and solid actives. It is compatible with solutions of up to 40 % ethanol. When used in combination with co-thickeners, it can be added to formulations containing > 60 % ethanol.

Recommended use

Creams and lotions	■
Sunscreen products	■
Depilatory creams	■
Shower gels and shampoos	■
Liquid makeup	■
Eye makeup	■

■ especially recommended □ recommended

Recommended levels

0.1–5 % additive (as supplied) based on the total formulation, depending on the application.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

LAPONITE-XLS XR should be added steadily to deionized water at a temperature of 15 to 25 °C under high shear within 10 to 30 seconds. It should be stirred fast enough that a turbulent vortex current is formed, so that the powder is well dispersed and clumps are avoided. After complete addition, stirring is continued for 20 minutes. At complete dispersion, a clear, colorless, and low-viscosity pre-mix is obtained. Once this pre-mix is combined with other components of the formulation, viscosity develops instantaneously. This can be affected by temperature, electrolytes, or pH value.

Special note

LAPONITE-XLS XR is not compatible with cationic compounds. For pH adjustment, citric acid, lactic acid, or sodium dihydrogen phosphate are recommended to lower the pH value and sodium hydroxide to increase the pH value. As the additive is a weak base and can thus lead to an increase in pH, it may be necessary to adjust the initial pH to a value below the target pH value.

Your local contact

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com