

**Data Sheet** Issue 09/2012

# **DISPERBYK-169**

Wetting and dispersing additive for solvent-borne, highly polar two-pack PU systems.

## **Product Data**

Composition **Aromatic-free** 

Solution of a high molecular weight block copolymer with pigment affinic groups

## **Typical Properties**

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value: 17.5 mg KOH/g Density (20 °C): 0.96 g/ml Non-volatile matter (20 min., 150 °C): 30 % Solvents: Butylacetate Flash point: 24 °C

## **Food Contact Legal Status**

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

#### **Special Note**

The additive is especially suitable for two-pack systems with hydroxyl values above 200. For optimum performance, the additive must be incorporated into the millbase before addition of pigments.

**BYK-Chemie GmbH** 46462 Wesel Germany Tel +49 281 670-0 Fax +49 281 65735

www.byk.com/additives

info@byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERBYK®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie.

AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany