Texicryl® 13-529

Acrylic Dispersions

Technical Data Sheet

Product Overview

TEXICRYL® 13-529 is a high performance styrene acrylic copolymer emulsion designed for use in cold seal adhesive formulations. TEXICRYL® 13-529 is APEO-free.

. Characteristics (Not to be taken as a specification)	
Solid Content (%)	50
pH	4.5
Viscosity (mPa.s) (Brookfield RVT, Spindle 2 @ 20 rpm, 25ºC)	200
Minimum Film Formation Temperature* (ºC)	12
Glass Transition Temperature (ºC)	19

✶ Determined by metal bar with temperature gradient.

Application

TEXICRYL® 13-529 is designed for use in cold seal adhesive formulations.

Packaging and Storage

TEXICRYL® 13-529 is supplied in 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL® 13-529 should be stored in the original, un-opened and undamaged containers in a dry place at temperature between 5ºC/41ºFand 30ºC/86ºF. Protect from freezing.

Health, Safety, and Regulatory

See separate Safety Data Sheet.

© 2022 Scott Bader Company Limited, July 2022, Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

Scott Bader Company Limited
Wollaston, Wellingborough, Northants NN29 7RL
44 (0)1933 663738
enquiries@scottbader.com