

Product information

ANQUAMINE[®] 724

Curing Agent

DESCRIPTION

Anquamine 724 is a waterborne curing agent for use with standard liquid epoxy resin. Anquamine 724 easily emulsifies standard liquid epoxy resins; the use of emulsifiable resins is not required.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber liquid		
Colour	max 12	Gardner	ASTM D 1544
Viscosity @ 25°C	15000-35000	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	250-280	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	1.05	g/ml	
Total Actives Content	60-64	wt %	
Equivalent Wt/{H}	200		
Recommended use Level	100-120	PHR	Cured with bisphenol-A based epoxy resin (EEW=190)

ADVANTAGES

- Excellent adhesion
- Fast drying times
- Good yellowing resistance
- Good flexibility
- Cement stable

APPLICATIONS

- Pigmented concrete coatings (100-300 µm)
- Concrete primers
- High gloss coatings

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers. Do not freeze.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Anquamine 724 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit	
Pot Life @ 23°C	60-120	min	
Thin Film Set Time @23 °C	3-4	h	ASTM D 5895 - BK Drying Recorder, Phase 3
Persoz Pendulum Hardness 1 day @ 23°C	280	s	ASTM D 4366
Persoz Pendulum Hardness 7 days @ 23°C	320	s	ASTM D 4366
Typical cure schedule	2 - 7	days	

Anquamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

