Texicryl® 13-067

Acrylic Dispersions

Technical Data Sheet

Product overview

TEXICRYL® 13-067 is a styrene acrylic copolymer emulsion designed for use in high performance roof coatings compounds and in a wide range of water-based paints.

Characteristics (Not to be taken as a specification)	
Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	11000 mPa s
pH	8.5
Minimum film formation temperature*	18°C
Glass transition temperature	29°C

*Determined by metal bar with temperature gradient

Application

TEXICRYL® 13-067 can be used in a range of emulsion paint formulations varying in properties from semi-gloss finish to high pigment volume concentration low cost paints. It is particulary suitable as a binder for high performance roofing compositions.

Packaging and storage

TEXICRYL® 13-067 maybe supplied in drums or IBC's (please check with your local representative).

Bulk deliveries are by road tanker.

TEXICRYL® 13-067 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost or direct sunlight should be avoided.

Health and safety

Please see separate material safety data sheet.

© 2021 Scott Bader Company Limited, March 2020, Issue No. 2

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER
Making a positive difference

Scott Bader Company Limited
Wollaston, Wellingborough, Northants NN29 7RL
44 (0)1933 663738
enquiries@scottbader.com