

BYK-3750

Silicone-containing surface additive for solvent-borne coating systems with a medium reduction in surface tension and a medium increase in surface slip.

Product Data

Composition

Solution of a polyether-modified polydimethylsiloxane

SVHC label-free
(EU SDS)

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.94 g/ml
Non-volatile matter (10 min., 150 °C):	52 %
Solvents:	Xylene/isobutanol 4/1
Flash point:	24 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Special Note

BYK-3750 is a low-cycle version of BYK-300. The cyclic siloxane content D4 / D5 / D6 is in each case less than 0.1 %, therefore the SVHC label is not required in the safety data sheet.

Applications

Coatings Industry

Special Features and Benefits

The additive provides a medium reduction in the surface tension of coating systems. It increases slip and improves leveling and gloss. Silicone additives prevent the formation of Bénard cells. BYK-3750 also improves substrate wetting and anti-blocking properties.

Recommended Use

BYK-3750 is broadly compatible and suitable for all solvent-borne systems.

Recommended Levels

0.1-0.3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition. Dilution before incorporation can make it easier to dose.

Special Note

Unlike so-called silicone oils, this additive is very user-friendly. However, before use, one should determine in a test series whether foam is stabilized in certain systems and check the recoatability and crater development.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany