

BYK-055

Silicone-free defoamer on polymer-basis for solvent-borne and solvent-free wood and furniture coatings.

Product Data

Composition

Solution of polyolefin

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.88 g/ml
Non-volatile matter (10 min., 150 °C):	6.5 %
Solvents:	Alkylbenzenes/Methoxypropyl acetate 12/1
Flash point:	45 °C

Applications

Coatings Industry

Special Features and Benefits

BYK-055 is especially effective in wood and furniture coatings based on glossy polyester, paraffin polyester, and in radiation curable polyester. The additive allows curtain coaters to maintain curtain stability even when only thin layers are applied. When using non-pigmented systems, a slight turbidity may be visible over dark wood. Good results were also found with epoxy systems.

Recommended Use

Solvent-borne und solvent-free wood and furniture coatings.

Recommended Levels

0.1-1.5 % additive (as supplied) based upon total formulation.

The dosage levels are indicated for the purpose of orientation. Optimal dosage levels are determined through series of tests.

Incorporation and Processing Instructions

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated at a later time, sufficient shear forces must be ensured in order to achieve good defoamer distribution and to prevent crater formation.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.