

Data Sheet Issue 10/2016

OPTIGEL-LX

Rheology additive based on an activated phyllosilicate for aqueous coating systems to generate thixotropic flow behavior.

Product Data

Composition

Activated phyllosilicate

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Specific density: 2.2 g/cm³ 580-730 kg/m³ Bulk density:

Moisture content: 6-12 % Supplied as: free-flowing, yellowish powder

pH value (2 % in H_2O): 10.5 ± 1

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

OPTIGEL-LX is hygroscopic and should be transported and stored dry in the unopened original container at temperatures between 0 °C and 30 °C.

Applications

Coatings Industry

Special Features and Benefits

OPTIGEL-LX generates thixotropic flow behavior. It improves processability and storage stability as it is highly effective at preventing solids settling. In addition, it reduces the sagging tendency after application which makes it possible to achieve greater layer thicknesses. OPTIGEL-LX is a mineral with a protective colloid and is stable to diluted acids and bases.

Recommended Use

OPTIGEL-LX is suitable for a variety of aqueous coating systems and particularly suitable for use in architectural coatings.

Architectural coating	S		
especially recommended	especially recommended		



OPTIGEL-LX

Data Sheet Issue 10/2016

Recommended Levels

0.5-1.2 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

OPTIGEL-LX is hydrophilic and easy to incorporate in water. To ensure optimum distribution and the best possible effectiveness and reproducibility in applications, the additive must be added to water (20 °C \pm 5 °C) slowly whilst stirring, and pre-dispersed at high shear forces for at least 20 minutes. OPTIGEL-LX should be fully hydrated before the remaining formulation components can be added to the dispersion. No wetting or dispersing additives are required to produce this dispersion. OPTIGEL-LX can be also be added to the formulation directly, as a powder at the start of manufacture.

Special Note

OPTIGEL-LX reacts sensitively to ions. If the mains water being used has a high total hardness, use deionized water for processing.







BYK-Chemie GmbH P.O. Box 10 02 45 46462 Wesel Germany
Tel +49 281 670-0 Fax +49 281 65735

info@byk.com www.byk.com ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKOZBLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.