

## DISPERBYK-182

Wetting and dispersing additive for aqueous and solvent-borne coating systems and printing inks. For all-purpose pigment concentrates of non-polar through to aqueous systems.

### Product Data

#### Composition

Solution of modified polyurethane

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	13 mg KOH/g
Density (20 °C):	1.03 g/ml
Non-volatile matter (20 min., 150 °C):	43 %
Solvents:	Methoxypropylacetate/methoxypropoxypropanol/butylacetate 7/4/4
Flash point:	38 °C

#### Special Note

The surface treatment of some organic pigments can negatively influence the effectiveness of the additive. In these cases, tests with the untreated pigment of the same type may be successful.

### Applications

#### Coatings Industry

##### Special Features and Benefits

DISPERBYK-182 deflocculates pigments by means of steric stabilization. As a result of the small particle size of the deflocculated pigments, high levels of gloss can be achieved and the color strength is optimized. Transparency and hiding power also increase and viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible.

##### Recommended Use

DISPERBYK-182 has a broad application spectrum and is suited to solvent-borne and aqueous systems. It is especially – alone or in combination with DISPERBYK-108 – used to produce particularly economical solvent-borne pigment concentrates.

##### Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments:	15-20 %
Titanium dioxides:	4-5 %
Organic pigments:	30-60 %
Carbon blacks:	80-100 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. Pre-mix the resin and solvent components of the millbase and then gradually let the DISPERBYK-182 flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed.

### Printing Inks

#### Special Features and Benefits

DISPERBYK-182 deflocculates pigments by means of steric stabilization. As a result of the small particle size of the deflocculated pigments, high levels of gloss can be achieved and the color strength is optimized. Transparency and hiding power also increase and viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible.

#### Recommended Use

DISPERBYK-182 has a broad application spectrum and is suited to solvent-borne and aqueous systems. It is especially – alone or in combination with DISPERBYK-108 – used to produce particularly economical solvent-borne pigment concentrates.

#### Recommended Levels

Amount of additive (as supplied) based upon pigment:

Titanium dioxides: 2.5-5 %

Organic pigments: 7-13 %

Carbon blacks: 7-13 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. Pre-mix the resin and solvent components of the millbase and then gradually let the additive flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed.



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.