

## BYK-306 SG

Silicone-containing surface additive for ambient-curing plastic systems and solvent-borne coating systems with a strong reduction of surface tension. Excellent substrate wetting, prevents cratering and increases surface slip.

### Product data

#### Composition

Solution of a polyether-modified polydimethylsiloxane

#### Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.93 g/ml
Non-volatile matter (30 min, 150 °C):	12.5 %
Solvents:	Xylene/monophenyl glycol 7/2
Flash point:	25 °C

#### Storage and transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

### Applications

#### Ambient Curing Plastic Systems

##### Special features and benefits

BYK-306 SG, a highly effective silicone additive, provides a strong reduction of surface tension. It thereby improves the wetting of critical substrates. In pigmented systems it can prevent the formation of Bénard cells and improve leveling.

##### Recommended use

BYK-306 SG is recommended for polyurethane and epoxy systems.

##### Recommended levels

0.1–0.5 % additive (as supplied) based upon total formulation. The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

##### Incorporation and processing instructions

The additive can be incorporated during any stage of the production process, including post-addition. It has proven successful to add the additive at the end of the process to avoid any foam stabilization.

##### Special note

Unlike so-called silicone oils, this additive is very user friendly. Nevertheless, before use it should be determined in series testing, whether surface defects occur in certain systems.

## Coatings industry

### Special features and benefits

The additive provides a strong reduction of the surface tension of the coating systems and is a highly effective silicone additive for wetting critical substrates. BYK-306 SG improves the acceptance of dust and spray mist and increases surface slip. It reduces air draft sensitivity in wood and furniture coatings and promotes the orientation of matting agents.

### Recommended use

The additive can be used in all solvent-borne systems.

### Recommended levels

0.1–0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

### Incorporation and processing instructions

The additive can be incorporated during any stage of the production process, including post-addition. Dilution before incorporation can make it easier to dose.

### Special note

Unlike so-called silicone oils, this additive is very user friendly. Nevertheless, before use it should be determined in a series of tests whether foam is stabilized in certain systems. Similarly the recoatability and cratering should be checked.



Your local  
contact

**BYK-Chemie GmbH**  
Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

info@byk.com  
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.