SYNOLITE™ 5750-A-5 - *DRAFT*

CHEMICAL/PHYSICAL NATURE

Synolite™ 5750-A-5 is a DCPD based, pre-accelerated, non-thixotropic, unsaturated polyester resin in styrene monomer.

MAJOR APPLICATIONS

It is designed for general casting applications and can be used specifically for shower tray casting behind a gel coat or primed ABS capped acrylic.

PRINCIPAL PROPERTIES

Synolite™ 5750-A-5 is a resilient resin with controlled exotherm. It is characterized by its high filler acceptance and rapid cure rate.

PRODUCT SPECIFICATIONS UPON DELIVERY

Property	Range	Unit	TM
Viscosity, 23°C	170 - 190	mPa.s	2013
Solids content, IR	63.5 - 66.5	%	2033
Gel time from 25 to 35°C	23 - 27	minutes	2625
Cure time from 25°C to peak	29 - 34	minutes	2625
Peak temperature	125 - 135	°C	2625

REMARKS

TM 2013: spindle Z2, speed 100 s-1, program
TM 2625: 1% in medium reactive MEKP

PROPERTIES OF THE LIQUID RESIN (TYPICAL VALUES)

Property	Value	Unit	TM
Stability, no init., dark,	3	months	-
Flash point	32	°C	2800

PROPERTIES OF CAST UNFILLED RESIN (TYPICAL VALUES)

Property	Value	Unit	TM
Tensile strength	40	MPa	ISO 527-2
Tensile E-modulus	3.3	GPa	ISO 527-2
Elongation at break	1.5	%	ISO 527-2
Flexural strength	80	MPa	ISO 178
Flexural E-Modulus	3.0	GPa	ISO 178
Heat Deflection Temp. (HDT)	82	°C	ISO 75-A
Hardness Barcol 934.1	42	Barcol	2604

CURING CONDITIONS

Casting cured overnight at ambient and post-cured for 2 hrs. at 90°C.

GUIDELINES BEFORE USE

Before use, the resin should be conditioned at a well-defined, application dependent temperature (usually 15°C minimum for a MEKP / Co cure). Stir the product before blending.

STORAGE GUIDELINES

The resin should be stored indoors in the original, unopened and undamaged packaging, in a dry place at temperatures between 5°C and 30°C and the properties might change during storage. Shelf life is reduced at higher temperatures and the properties of the resin might change during storage. The shelf life of styrene containing unsaturated polyesters will be significantly reduced when exposed to light. Store in dark and in 100% light tight containers only.
With DCPD resins there is a tendency for skin formation if exposed to air. Whilst products are formulated to reduce this characteristic, exposure to air and ventilation in bulk storage facilities should be minimized.

MATERIAL SAFETY

A Material Safety Data Sheet of this product is available on request.

TEST METHODS

Test methods (TM) referred to in the table(s) are available on request.

Aliancys is a leading global company active in the sales of Quality Resins for composite applications. Together with its customers, Aliancys is pushing the limits of both composite part manufacturing and performance. Taking an integral approach to new product development, Aliancys is using its full expertise in resin chemistry, material science, and component manufacturing for shaping new applications in composites. So let's talk and increase our mutual business success, both today and tomorrow. More information on **www.aliancys.com**

PRODUCT INQUIRY? PLEASE CLICK HERE

The user is held to check the quality, safety and other properties of the product referred to herein. The information and recommendations in this document are to the best of our knowledge and reliable. However, no rights whatsoever can be derived from this document or the information contained therein by any party, other than those expressly accepted by a selling entity of the Aliancys group of companies ("Aliancys selling entity") in a binding sale and purchase agreement for product referred to herein. For the avoidance of doubt the Aliancys group of companies makes no warranty of any kind, express or implied, including those of merchantability and fitness for purpose. Unless explicitly agreed to otherwise in writing by the Aliancys selling entity, all offers, quotations, sales and deliveries of Aliancys products are subject to the general conditions of sale of such Aliancys selling entity.
Atlac®, Beyone™, Daron®, Neomould®, Neoxil®, Palatal®, Palapreg®, Synolite™, Aliancys™, the Aliancys™ logo, and the LET'S TALK/ logo are registered trademarks of Aliancys AG.
For more information: www.aliancys.com

aliancys QUALITY RESINS