

# DISPERBYK-194 N

Wetting and dispersing additive for aqueous systems and pigment concentrates, especially for use in aqueous two-pack polyurethane and two-pack epoxy systems.

## Product Data

### Composition

Solution of modified carboxyl functional polyglycol copolymer

Aromatic-free

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 75 mg KOH/g  
Density (20 °C): 1.08 g/ml  
Non-volatile matter (10 min., 150 °C): 57 %  
Solvents: Water

### Storage and Transportation

Separation or turbidity may occur at temperatures below 10 °C. Warm to 20 °C and mix well.

## Applications

### Coatings Industry

#### Special Features and Benefits

The additive deflocculates pigments through steric stabilization of the pigments. Due to the small particle size of the deflocculated pigments, high gloss is achieved and the color strength is improved. In addition, this product increases the transparency and hiding power of pigments and reduces viscosity. Subsequently, it improves leveling and allows for higher pigment loading.

#### Recommended Use

DISPERBYK-194 N is used for the production of pigment concentrates with or without resins and for pigment grinding in aqueous coatings. It is especially recommended for use with aqueous two-pack PU and two-pack epoxy systems. Pigment concentrates formulated with DISPERBYK-194 N can be incorporated into amine components as well as epoxy resins.

Industrial coatings	■
Wood and furniture coatings	■
Protective coatings	■

■ especially recommended

## Recommended Levels

Amount of additive (as supplied) based upon pigment

Inorganic pigments:	15-35 %
Titanium dioxide:	7-13 %
Organic pigments:	30-90 %
Carbon black:	100-150 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

For optimal performance in systems containing resins, the additive should be slowly incorporated into the aqueous resin while agitating the mixture. For pigment concentrates without resins, simply mix the additive with water. Add pigments only after the additive is homogeneously distributed.

## Special Note

Pigment concentrates formulated with DISPERBYK-194 N must be neutralized before being added to let-down.



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.