

BYK-4512

Adhesion promoter for solvent-borne systems applied to metal substrates.

Product Data

Composition

Solution of aminofunctional polyether

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	56 mg KOH/g
Density (20 °C):	1.10 g/ml
Non-volatile matter (20 min., 150 °C):	60 %
Solvents:	Methoxypropylacetate
Flash point:	43 °C

Applications

Liquid coatings

Special Features and Benefits

In coil coatings, BYK-4512 improves adhesion after water immersion and forming processes, for example deep-drawing, T-bend, and corrosion resistance. It is particularly well-suited for use in chromate-free primers and on metal substrates that are pre-treated in a chromate-free manner. BYK-4512 reacts with melamine resins and polyisocyanates and is cross-linked into the polymer matrix. In industrial coatings, BYK-4512 improves the adhesion of coatings, which are applied directly onto metal or glass. The additive is particularly well-suited for use in 2K systems and baking coatings.

Recommended Use

Coil Coatings	■
Industrial Coatings	■

■ particularly recommended

Recommended Levels

1-4 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of tests. As a reference point, a dosage of 1.7 % additive in delivery form on the total formulation can be started with.

Incorporation and Processing Instructions

The additive can be incorporated at any time during paint production with moderate shear forces.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.