

Product Information

VESTAMID® NRG 4901 black

For Steel Pipe Protection (Encasement)

VESTAMID® NRG 4901 black offers a flexible, mechanically tough encasement system that combines the advantages of polyethylene coating and cement mortar casing.

Uses of VESTAMID® NRG products

The important advantages of VESTAMID® NRG 4901 as an encasement material are:

- unusually high impact resistance and toughness, even at low temperatures
- excellent stress cracking resistance
- excellent wear resistance
- low sliding friction coefficient

Product characteristics compared with other encasement materials

VESTAMID® NRG 4901 has higher Shore hardness than polyethylene or polypropylene. In contrast to polyethylene or propylene encasement, therefore, the polyamide encasement offers, apart from the corrosion protection provided by the barrier effect, also mechanical protection for the encased steel pipe.

Application areas for the new encasement material are found in non-conventional installation technologies such as:

- horizontal directional drilling
- the soil displacement method with non-steered displacement hammers
- dynamic ramming
- plow technology

We recommend a processing temperature between 230°C (446°F) and 260°C (500°F) – in some cases up to 280°C (536°F) – during the extrusion process.

Drying at 80°C (176°F) for 2 hours to 4 hours before processing is recommended.

For information about processing of VESTAMID® NRG 4901 please follow the general recommendation in our brochure „VESTAMID® Processing Guide Line.“

For further information, please contact us at evonik-hp@evonik.com.

Property	Test method		Unit	VESTAMID® NRG 4901 black	
	international	national			
Density	23°C / 73°F	ISO 1183	DIN EN ISO 1183	g/cm³	1.02
Melting range		ASTM D3418			
DSC	2 nd heating			°C / °F	177 / 351
Tensile test	ISO 527-1	DIN EN ISO 527-1			
Stress at yield	ISO 527-2	DIN EN ISO 527-2	MPa	40	
Strain at yield			%	12	
Strain at break			%	> 150	
Tensile modulus	ISO 527-1	DIN EN ISO 527-1	MPa	1350	
	ISO 527-2	DIN EN ISO 527-2			
CHARPY impact strength	ISO 179/1eU	DIN EN ISO 179/1eU			
	-40°C / -40°F		kJ/m²		N ¹⁾
Shore hardness D	ISO 868	DIN EN ISO 868		73	
Ball indentation hardness H30	ISO 2039-1	DIN EN ISO 2039-1	N/mm²	76	
Vicat softening temperature	ISO 306	DIN EN ISO 306			
Method A	10 N		°C / °F	170 / 338	

¹⁾ N = No break

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

® = registered trademark

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. Evonik shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.