

BYK-1818

PFAS-free, silicone-containing defoamer for solvent-borne and solvent-free coating systems.

Product data

Composition

Solution of polysiloxanes

PFAS-free

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.88 g/ml
Non-volatile matter (10 min, 150 °C):	1 %
Solvents:	Butyl acetate
Flash point:	26 °C

Applications

Coatings industry

Special features and benefits

BYK-1818 is a highly effective defoamer for solvent-borne and solvent-free coating systems. Even at low dosing levels, optimal and spontaneous defoaming can be achieved.

Recommended use

Architectural coatings	<input type="checkbox"/>
Floor coatings	<input type="checkbox"/>
Wood and furniture coatings	<input type="checkbox"/>
General industrial coatings	<input type="checkbox"/>
Marine coatings	<input checked="" type="checkbox"/>
Protective coatings	<input checked="" type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended levels

0.1–1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated later, sufficient shear forces must be applied to ensure a good defoamer distribution and to prevent crater formation.

**Your local
contact****BYK-Chemie GmbH**
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735**info@byk.com**
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK®-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.