

## Product Information

# Dynasylan® SIVO 140

**Water-borne inorganic-organic binder for two-pack zinc dust paints**

## PRODUCT DESCRIPTION

Dynasylan® SIVO 140 is an acidic silane based, fully hydrolysed and almost VOC-free binder. It can be thinned with water or water-soluble organic solvents.

### Typical Properties

Property	Unit	Value
<b>Chemical Name</b>		Water-borne inorganic-organic binder
<b>Density</b> DIN 51757	g/cm <sup>3</sup>	1.08-1.10
<b>pH Value</b> DIN 38404-C5		3-4.5
<b>Viscosity</b> DIN 53015	mPa·s	1-10

The data represents typical values (no product specification)

## TYPICAL APPLICATIONS

Dynasylan® SIVO 140 can be formulated with fillers and pigments. Formulations based on Dynasylan® SIVO 140 cure at room temperature.

### Product Composition

Product Composition	Unit	Value
<b>Silicon Dioxide (SiO<sub>2</sub>) Content</b>	wt%	13.0-15.5
<b>Solids Content</b> 3 g/ 2 h 105 °C	wt%	21.5-23.5

The data represents typical values (no product specification)

## BENEFITS & ADVANTAGES

The advantages of Dynasylan® SIVO 140 formulations include:

1. improved heat resistance compared to organic binders
2. almost zero VOC
3. room temperature curing
4. low or higher film thicknesses are possible
5. good adhesion of top coats

Dynasylan® SIVO 140 is water-borne and therefore more environmentally friendly than traditional zinc silicate coatings based on silicic acid esters.

## HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

## PACKAGING

Dynasylan® SIVO 140 is supplied in 25 kg PE drums and 200 kg PE-inlined steel drums and 970 kg IBC containers.

## STORAGE

Due to its water content Dynasylan® SIVO 140 must be stored above freezing temperature. Storage temperatures must not exceed 40 °C.

## SHELF LIFE

In sealed containers Dynasylan® SIVO 140 has a shelf life of min. 12 months from delivery.

#### Registration Listings

Registry	Status
Australia (AIIC)	Information on Request
Canada (DSL)	Information on Request
China (IECSC)	Information on Request
EU (EINECS/ELINCS)	Yes
Japan (ENCS)	Information on Request

#### Registration Listings

Registry	Status
South Korea (KECL)	Information on Request
Philippines (PICCS)	Information on Request
USA (TSCA)	Information on Request

#### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

#### Evonik Operations GmbH

Smart Effects  
Rodenbacher Chaussee 4  
63457 Hanau  
Germany  
ask-se@evonik.com  
ask-se-asia@evonik.com  
ask-se-america@evonik.com  
[www.evonik.com/smarteffects](http://www.evonik.com/smarteffects)