

CLAYTONE-VP V

Powdered rheology additive based on an organophilic phyllosilicate for non-polar to medium-polar systems to produce a thixotropic flow behavior.

Product Data

Composition

Organophilic phyllosilicate

Organic plant-based
post-treatment

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density: 400-600 kg/m³

Water content: max. 5 %

Specific weight: 1.8 g/cm³

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

CLAYTONE-VP V should be transported and stored dry in the unopened original container at temperatures between 0 °C and 30 °C.

Applications

Lubricating oils and greases

Special Features and Benefits

CLAYTONE-VP V can be used as a thickener in low-polar to medium-polar oils. The product requires the use of an activator in order to guarantee the complete separation of the platelets (complete dispersion of agglomerates to primary particles) and to ensure optimum effectiveness. The product swells in organic media and results in a gel structure. Weak hydrogen bridge bonds are the reasons for the thixotropic flow behavior. The special feature of CLAYTONE-VP V is the entirely plant-based organic post-treatment.

Recommended Use

CLAYTONE-VP V can be used as a thickener in low-polar to medium-polar oils.

Recommended Levels

Lubricating oils:

1-4 % CLAYTONE-VP V for an increase in the viscosity with thixotropic flow behavior and anti-settling properties.

Greases:

5-7 % CLAYTONE-VP V for NLGI classes 1 to 2 in mineral oils.

The above recommended levels can be used for orientation. Optimal levels are determined through a demarcating series of laboratory tests.

Incorporation and Processing Instructions

The additive requires a high shear forces and a polar activator to separate the phyllosilicate platelets and disperse them fully. High-shear equipment such as a colloid mill should be used for processing.

As an activator, it is recommended to use approx. 20 % (referring to CLAYTONE-VP V) of, for example,

- propylene carbonate or propylene carbonate/water (95/5)
- methanol or methanol/water (95/5)
- ethanol or ethanol/water (95/5)



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany