

BYK-SYNERGIST 2105

Pigment synergist for solvent-borne and solvent-free coating systems. Improves the effectiveness of polymeric wetting and dispersing additives when stabilizing organic yellow, orange and red pigments.

Product Data

Composition

Insoluble pigment complex

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.11 g/ml
Non-volatile matter: 100 %
Melting point: 155 °C
Moisture content: 2 %
Supplied as: Powder

Applications

Coatings Industry

Special Features and Benefits

The synergist enables high-molecular weight wetting and dispersing additives to be more efficiently adsorbed on the surface of organic yellow, orange and red pigments, thereby increasing the effectiveness of the wetting and dispersing additives. Stabilization of the pigments is improved and higher pigment contents are possible as a result of a reduction in the viscosity.

Recommended Use

The synergist is always used in combination with high-molecular weight wetting and dispersing additives and is recommended for coatings and pigment concentrates.

Recommended Levels

Additive dosage as supplied based on pigment:

Organic yellow pigments (e.g. PY 154, PY 110): 2-4 %
Organic orange pigments (e.g. PO 36, PO 62): 2-4 %
Organic red pigments (e.g. PR 179, PR 254): 3-5 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the powdered synergist must be incorporated in the millbase together with polymeric wetting and dispersing additives prior to adding the pigments.

BYK-SYNERGIST 2105

Data Sheet
Issue 08/2021



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.