

## ANTI-TERRA-204 SG

Controlled flocculating wetting and dispersing additive for solvent-borne medium-polar to non-polar thick layer systems and primers to prevent fillers and inorganic pigments from settling and to gel bentonites.

### Product data

#### Composition

Solution of a polycarboxylic acid salt of polyamine amides

#### Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.93 g/ml
Non-volatile matter (20 min, 150 °C):	52 %
Solvents:	Methoxypropanol/alkylbenzenes 3/2
Flash point:	31 °C
Acid value:	41 mg KOH/g
Amine value:	37 mg KOH/g

### Applications

#### Coatings industry

##### Special features and benefits

The additive acts by controlled flocculating the pigments. This also prevents sagging and keeps the pigments from settling as well as flooding and floating. ANTI-TERRA-204 SG is also suitable for non-polar systems (white spirit compatible), in contrast to ANTI-TERRA-203 SG. The lower the polarity, the stronger the thixotropic effect will be. Long, middle, and short oil alkyds, PVC copolymers, chlorinated rubber and epoxies are the preferred binders. It can often improve anticorrosive properties when used in protective coating primers.

##### Recommended use

Especially recommended applications: Industrial coatings, wood and furniture coatings, protective coatings.  
Recommended application: Architectural coatings.

##### Recommended levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments:	1–2 %
Titanium dioxide/Fillers:	0.5–1 %
Bentonites:	30–50 %

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

**Incorporation and processing instructions**

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. It is also suitable for retroactive batch correction, however, for this application the performance is somewhat lower.

The following suggested formulation can be used to gel bentonites:

85–87 parts (by weight) solvents  
10 parts (by weight) bentonites  
5–3 parts (by weight) additive

The solvent can be aromatic or aromatic white spirit, although aromatic-free white spirit is also suitable. If the gelling effect is not sufficient, polar solvents may be added to increase it.

**Special note**

Discolorations may occur in coatings based on cellulose nitrate, chlorinated rubber, and PVC copolymers. Silicate coatings have a shortened pot life. High levels may affect pot life and curing in epoxy systems. The additive's high amine value can lead to increased viscosity in the epoxy resin.

**Thermosets****Special features and benefits**

The additive derives its benefits from the systematic, controlled flocculation of fillers and chips, which primarily prevents these particles from settling. This allows ANTI-TERRA-204 SG to facilitate a more homogeneous distribution of fillers and chips in acrylic systems. The additive prevents settling, which achieves a more even surface structure when using chips.

**Recommended use**

Especially recommended for ambient curing acrylic systems (PMMA in MMA) and in all pultrusion resin systems, including UP, VE, acrylic and epoxy.

**Recommended levels**

0.5–1.5 % additive (as supplied) based upon fillers.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

**Incorporation and processing instructions**

For optimal performance, the additive should be incorporated before solids are added.



Your local  
contact

**BYK-Chemie GmbH**  
Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

info@byk.com  
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.