SCOTT BADER
Making a positive difference

Texicryl® 13-223

Acrylic Dispersions

Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-223 is self crosslinking styrene acrylic copolymer emulsion with high solvent and dry clean resistance.

CHARACTERISTICS (Not to be taken as a specification)	
Solids content	45%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	100 mPa s
pH	6.0
Particle size	210 nm
Minimum film formation temperature*	<2 °C
Glass transition temperature	11°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-223 is used in textile and non woven applications where a medium soft handle is required.

PACKAGING AND STORAGE

TEXICRYL 13-223 is be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-223 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

SCOTT BADER
Making a positive difference

Scott Bader UK Office
Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738
email: enquiries@scottbader.com

© 2020 ScottBader Co Ltd, September 2020 | Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.