

BYK-C 8000

Reactive, polymeric coupling agent (adhesion promoter) to improve mechanical properties in radical curing systems. Plastic applications are polymer concrete and solid surfaces; preferably in quartz- and granite-filled resins. In solvent-borne and solvent-free coatings, the additive acts as an adhesion promoter on metal and glass.

Product Data

Composition

Solution of modified polyether

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value: 15 mg KOH/g

Density (20 °C): 0.99 g/ml

Storage and Transportation

To be stored and transported at a temperature below 40 °C. Moisture sensitive.

Applications

Ambient Curing Resin Systems

Special Features and Benefits

BYK-C 8000 improves the mechanical properties such as flexural strength, compressive strength and the E modulus by up to 50 %. The additive is recommended for radical curing systems such as polymer concrete, solid surfaces, preferably in quartz- and granite-filled resins.

Recommended Levels

0.1-0.3 % additive (as supplied) based upon the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added to the resin shortly before the curing process. After the addition, the resin system needs to be processed within a maximum of 24 hours. The time span varies depending on the type of resin and additive quantity.

Coatings Industry

Special Features and Benefits

In solvent-borne and solvent-free coatings, BYK-C 8000 can substantially improve adhesion to substrates such as pre-treated steel and also glass. In the tested formulations, the additive showed no negative impact on standard coating properties. The additive is recommended for reactive acrylate systems, baking coatings (e.g. acrylic/melamine) and for UV systems.

Recommended Levels

Max. 1 % additive (active substance) based upon the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added to the coating at any stage of the production process whilst stirring.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.