

# **AQUAMAT 272 N**

Matting wax dispersion based on modified PE for aqueous coatings, as well as printing inks and overprint varnishes for improved surface protection.

# **Product Data**

#### Composition

Dispersion of modified polyethylene wax

# **Typical Properties**

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (60 min., 125 °C): 55 % Carrier: Water Melting point (wax content): 125 °C Particle size (Hegman): 30  $\mu$ m Viscosity (23 °C, D=800/s): < 500 mPa·s

pH value:

# **Food Contact Legal Status**

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

# **Storage and Transportation**

Temperature sensitive. To be stored and transported between 5 °C and 35 °C. Mix well before use.

#### **Special Note**

In opened containers, the additive can dry out on the inner wall of the container. Such dried-out additive residue can lead to defects in the final product, and therefore the additive must be homogenized and filtered prior to use.

# **Applications**

# **Coatings Industry**

#### **Special Features and Benefits**

The additive increases surface protection and has a matting effect.

#### **Recommended Use**

Architectural coatings	
Wood and furniture coatings	
Industrial coatings	
Leather finishes	

lacksquare especially recommended lacksquare recommended



#### **AQUAMAT 272 N**

**Data Sheet** Issue 04/2019

# **Recommended Levels**

1-6% additive (as supplied) based on the total formulation, depending on the desired degree of matting.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### **Incorporation and Processing Instructions**

The additive is preferably incorporated into the coating at the end of the production process with a low shear rate. Mix well before use.

# **Printing Inks and Overprint Varnishes**

#### **Special Features and Benefits**

The additive increases abrasion resistance, and has a matting effect.

# **Recommended Levels**

1-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

# **Incorporation and Processing Instructions**

The additive is preferably incorporated into the coating at the end of the production process with a low shear rate. Mix well before use.







BYK-Chemie GmbH O. Box 10 02 45 46462 Wesel Germany Tel +49 281 670-0 Fax +49 281 65735

info@byk.com www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET® ACIAL\*, ADD-MAX\*, ADD-VANCE\*, ADJUST\*, ADVINCLE\*, ANTI-TERRA\*, AQUACER\*, AQUACER\*, AQUACER\*, BYROZITE\*, BYR\*, BYR\*-LYNWET\*, BYR\* are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments