

ANCAMIDE® 2769

Curing Agent

DESCRIPTION

Ancamide 2769 curing agent is an innovative technology designed for use with liquid epoxy resin. Showing polyamide like properties it is also 100% solids, contains no plasticizer and exhibits very low viscosity. This allows for formulation of solvent free or high solids coatings with ultra low volatile organic components.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear amber liquid		
Colour	≤ 10	Gardner	ASTM D 1544
Viscosity @ 25°C	100-160	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	400-440	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	0.97		
Equivalent	150	Wt/{H}	
Recommended use Level	65-80	PHR	With bisphenol-A based epoxy resin (EEW=190), 80 phr

ADVANTAGES

- Very low viscosity
- 100% Solvent and plasticizer free
- Excellent compatibility with liquid epoxy resin
- No induction time
- Good through cure and appearance at 10°C
- Good corrosion resistance

APPLICATIONS

- High solids and solvent free marine and maintenance coatings
- General protective coatings
- Tank and container coatings

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 2769 curing agent.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit	Method
Gel Time @ 25°C	120	min	Techne GT-3 Gelation Timer, 150 g mix
Thin Film Set Time @ 25°C	9	h	ASTM D 5895 - BK Drying Recorder, Phase 3
Thin Film Set Time @ 10°C	24	h	ASTM D 5895 - BK Drying Recorder, Phase 3
Persoz Hardness 1/7d @ 25°C	205/300	s	ASTM D 4366
Typical cure schedule	2-7	days	

* With bisphenol-A based epoxy resin (EEW=190), 80 phr

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

