

## BYK-3400

Silicone-containing substrate wetting additive for aqueous coatings, adhesives and maintenance products to reduce the surface tension. Good substrate wetting, no increase in the surface slip.

### Product data

#### Composition

Aqueous solution of a modified succinic acid and polyether-modified siloxane

#### Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.08 g/ml

Active substance: 70 %

Solvents: water

### Applications

#### Coatings industry

##### Special features and benefits

The additive causes a considerable reduction in the surface tension in aqueous coatings and thus especially improves substrate wetting and leveling. It only marginally, if at all, stabilizes foam and the recoatability is not impaired. The additive does not increase the surface slip. If a greater surface slip is required, we recommend that it is combined with a polysiloxane such as BYK-333.

##### Recommended levels

0.5–2 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

##### Incorporation and processing instructions

It is preferable to add the additive to the already completed coating. However, it can be used at any stage during the coating manufacture.

## Adhesives and sealants

### Special features and benefits

BYK-3400 reduces the surface tension in aqueous adhesive systems. It thereby improves the wetting of critical substrates. It only marginally, if at all, stabilizes foam.

### Recommended levels

0.5–2 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

### Incorporation and processing instructions

It is preferable to add the additive to the already completed formulation. However, it can be used at any stage during manufacture.

## Care products and polishes

### Special features and benefits

BYK-3400 reduces the surface tension and therefore improves the substrate wetting and leveling in aqueous maintenance products. It only marginally, if at all, stabilizes the foam, does not impair the subsequent layer and does not increase the surface slip.

### Recommended use

The additive is particularly recommended for self-shine emulsions (matt and gloss), wax cleaning agents and semi-aqueous cleaning agents with a plasticizer content in excess of 5 %.

### Recommended levels

0.05–1 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

### Incorporation and processing instructions

It is preferable to add the additive to the already completed formulation. However, it can be used at any stage during manufacture. Prior to use in systems containing plasticizers, the additive should be diluted using the volatile plasticizer to 10 % non-volatile matter.



**BYK-Chemie GmbH**  
Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

info@byk.com  
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK®-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.