

DISPERBYK-161

Wetting and dispersing additive for solvent-borne automotive and industrial coatings and pigment concentrates. Particularly suitable for stabilizing carbon blacks with a fine particle size as well as organic pigments, especially in two-pack PU and baking systems. Outstanding reduction of millbase viscosity.

Product Data

Composition

Solution of modified polyurethane

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	11 mg KOH/g
Density (20 °C):	1.02 g/ml
Non-volatile matter (20 min., 150 °C):	30 %
Solvents:	Methoxypropylacetate/Butylacetate 6/1
Flash point:	38 °C

Storage and Transportation

Separation or turbidity may occur at temperatures below 0 °C. Warm to 20 °C and mix well.

Special Note

The after-treatment of some organic pigments may negatively affect the efficiency of the additive. In such cases, tests with the untreated pigment of the same type may be successful. When used in coil coatings, the interaction of this cationic additive with the acid catalyst must be taken into account. Amine-blocked acids are less suitable than free acids or epoxy-blocked acids. This problem can be avoided by using additives from the DISPERBYK-170 product line.

Applications

Coatings Industry

Special Features and Benefits

The additive deflocculates pigments and stabilizes them by means of steric hindrance. It provides equal electrical charge to the pigment particles. The resulting repulsion and the steric stabilization prevent a possible co-flocculation, which leads to flood and float-free color in pigment mixtures. The deflocculating properties of the additive increase gloss, color strength, transparency, and hiding power and reduce the viscosity of the millbase.

Applications

Automotive coatings	☒
Industrial coatings	☒
Architectural coatings	☐
Protective coating systems	☐

☒ especially recommended ☐ recommended

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 10-15 %
 Titanium dioxide: 5-6 %
 Organic pigments: 30-90 %
 Carbon blacks: 70-140 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.



BYK-Chemie GmbH
 P.O. Box 10 02 45
 46462 Wesel
 Germany
 Tel +49 281 670-0
 Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.