

BYK-356

Polyacrylate-based surface additive for solvent-borne and solvent-free coatings and powder coatings to improve leveling. Solvent-free version of BYK-355.

Product Data

Composition

Polyacrylate

Solvent free

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.05 g/ml

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Special Note

The additive is thermally stable up to approx. 240 °C.

It is also available under the name BYK-355 as a 52 % solution in methoxypropylacetate.

Applications

Liquid Coatings

Special Features and Benefits

The additive is used as an anti-cratering and leveling additive in all solvent-borne and solvent-free coatings. It increases gloss and produces a long wave effect. It reduces the surface tension only to a slight extent, and does not impair the recoatability and the intercoat adhesion.

Recommended Levels

0.05-0.7 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Powder coatings

Special Features and Benefits

The additive combines the best anti-cratering effect with optimum leveling and DOI (distinctness of image). Fish eyes and pinholes in the powder coating layer are prevented. It does not cause haze in pigmented powder coatings and does not cause turbidity in powder clear coats. Its low viscosity and good compatibility enable easy incorporation in the resin when producing the master batch.

Recommended Use

The additive is recommended for manufacturing resin master batches for powder coatings, especially for powder clear coats.

Recommended Levels

0.5-15 % additive (as supplied) based on the resin.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is added to the powder coating resin at the end of the manufacturing process and mixed with the resin.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45

46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany