Data Sheet Issue 10/2017

CERAFLOUR 994

Micronized additive based on an amide wax for solvent-borne coating systems and powder coatings. To improve scratch resistance and sandability, electrostatic charge of powder coatings and meat release properties in can coatings.

Product Data

Composition

Ultra-fine micronized amide wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density: 0.99 g/cm³ Melting point: 145 °C

Particle size distribution (laser diffraction, volume distribution): D50: 5 μm D90: 10 μm

Supplied as: Micropowder

Food Contact Legal Status

This additive is suitable for applications with food contact. For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

Applications

Powder Coatings

Special Features and Benefits

The additive improves the pigment wetting in the manufacture of powder coatings and the electrostatic charge during application.

Recommended Use

CERAFLOUR 994 is recommended for powder coatings based on polyester, polyester/epoxide, acrylate, polyurethane and epoxides.

Recommended Levels

 $0.5-2\,\%$ additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

CERAFLOUR 994 should be mixed with resin, hardener, pigments and other additives using a high-speed mixer and extruded along with all components.

CERAFLOUR 994

Data Sheet Issue 10/2017

Liquid Coatings

Special Features and Benefits

The additive improves scratch resistance and sandability and reduces the gloss in all solvent-borne and solvent-free coating systems. Meat release properties in can coatings are improved.

Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process at a moderate shear rate.







BYK-Chemie GmbHP.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com www.byk.com ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKOZBLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.