

Product Information

Dynasylan® F 8261

Fluoralkylsilane

PRODUCT DESCRIPTION

Dynasylan® F 8261 is a bifunctional silane possessing hydrolyzable inorganic ethoxysilyl groups and a fluoroalkyl chain.

Dynasylan® F 8261 acts as a surface modifier on mostly hydroxyfunctional substrates (e.g. glass, ceramic). It can also be used as an adhesion promoter between inorganic materials and fluoropolymers (PTFE, fluorosilicones etc.). Dynasylan® F 8261 is a colorless and odorless liquid. It can be diluted to a proportion of about 25 wt.-% in ethanol and various other organic solvents, e.g. n-hexane, xylene, acetone or ethyl acetate.

Property	Unit	Value
Boiling Point, min.	°C	220
(1.013 hPa) DIN 51751		
Chemical Name		Tridecafluoroctyl- triethoxysilan,
Density	g/cm³	1.334
(20 °C) DIN 51757		
Flash Point, min.	°C	108
DIN EN ISO 2719		
Melting Point	°C	<-38
DIN ISO 3841		
pH Value		5.5
(20 °C, 1:1 in H2O), DIN 19268		
Viscosity	mPa·s	3.5
(20 °C) DIN 53015		

TYPICAL APPLICATIONS

Dynasylan® F 8261 can be applied in a wide variety of commercially important applications: Examples include:

- Treatment of automotive glass ("wiperless windshield")
- Easy-to-clean, water-repellent, UV-resistant coating of float glass (constructive glazing)
- · Additive for sol-gel systems
- Synthesis of fluorosilicones
- · Coating of pigments (e.g. in cosmetics)
- CVD processes
- Easy-to-clean coating on ceramics

DOSAGE

Processing:

Surfaces must be absolutely clean and degreased before treatment!

E.g. the glass surface can be ideally activated with cerium oxide.

for example:

- Glass treatment (e.g. on automotive glass)

The silane is typically diluted to about 1 wt.-% in a suitable solvent (e.g. isopropanol) after 2-10 wt.-% of distilled water and 0.2 wt.-% of hydrochlorid acid) are added. The solution is stirred for about 5 hours and should then be used within one day. substrate treatment can be carried out by dipping, spraying, rinsing, painting or polishing.

The obtained polysiloxane film is completely invisible and will not lead to any optical impairment on the substrate.

HANDLING & PROCESSING

In the presence of water, the ethoxy groups of Dynasylan® F 8261 hydrolyze to produce ethanol and form reactive silanol groups which can bond to a variety of inorganic substrates. The fluoroalkyl functional group provides a low energy surface.

Hydrophobic and oleophobic surface properties can also be achieved by treatment with commercial fluorocarbon surfactants and resins. However, Dynasylan® F 8261 has an



distinct advantage: The formation of a Si-O-substrate bond and subsequent horizontal crosslinking, which takes place upon evaporation of the solvent. This process leads to the formation of 2- and 3-dimensional networks.

Thus starting from very low concentrations Dynasylan® F 8261 is able to form chemically and mechanically stable coatings which exhibit a thickness of only a few nanometers. Suitable substrates include glass, silica, quartz powder, sand, sandstone, cristobalite, wollastonite, mica, kaolin, talc, and other silicate surfaces.

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website https://silanes.evonik.com/en or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® F 8261 is supplied in drums containing 200 kg.

Pails (10 kg & 25 kg) are available as MTO.

SHELF LIFE

In the unopened container, the shelf life of Dynasylan® F 8261 is min. 12 months from delivery.

Registration Listings	
Registry	Status
Australia (AIIC)	Yes
Canada (DSL)	Information on Request
China (IECSC)	Yes
EU (REACH)	Yes
EU (EINECS/ELINCS)	Yes
Japan (ENCS)	Information on Request
South Korea (KECL)	Yes
Philippines (PICCS)	No
USA (TSCA)	Yes
for professional or industrial use only! No consumers. Please see 40CFR721.3	3.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
www.evonik.com/smarteffects

