

Product Information

Dynasylan® SILBOND® Pure

Tetraethyl orthosilicate 99.0 %

PRODUCT DESCRIPTION

Dynasylan® SILBOND® Pure is a clear, low-viscosity liquid that is essentially pure tetraethyl orthosilicate monomer (99.0%). Dynasylan® SILBOND® Pure is used as a building block for zeolites and catalyst carriers, crosslinking agent, chemical intermediate, clear-coat component, and in any other application requiring pure TEOS monomer.

Typical Properties

Property	Unit	Value
Appearance		Clear Liquid
Boiling Point, min.	°C	167
Chemical Name		Tetraethyl orthosilicate 99.0 %
Density (20 °C)	g/cm ³	0.932-0.936
Flash Point, min.	°C	53
Product Purity, min. (GC-TCD); % wt min. QC07114P	%	99.0
Viscosity (20 °C)	mPa·s	0.75

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dynasylan® SILBOND® Pure can replace Dynasylan® SILBOND® Condensed in every application, where higher purity is needed. Dynasylan® SILBOND® Pure is a ready source of silicic acid for many applications. Silicic acid is usually obtained by hydrolysis, or thermally by condensation at elevated temperatures.

The resulting silicic acid bonds well to many inorganic substrates and can be deposited in-situ in a controlled manner. The surfaces of glass, metals, pigments, fillers, and synthetic fibers can be coated with a very thin SiO₂ layer in

order to improve chemical and thermal stability, and mechanical properties.

Other applications are:

- building blocks for zeolites and catalyst carriers
- raw material for optically clear coatings
- binders for fillers in inorganic zinc-rich paints or precision investment castings
- crosslinkers in silicone rubber systems
- drying agents in sealant compositions

Dynasylan® SILBOND® Pure is an important starting material for sol-gel processes, where the additional use of alkylalokoxysilanes (e.g. Dynasylan® MTES) can give the siloxane network a slight organic character as a result of the incorporation of alkyl groups.

It is also possible to construct an inorganic/organic network by adding silanes containing organofunctional groups (e.g. aminopropyl groups) and polymerizing with organic precursors. This principle makes it possible to obtain highly scratch- and abrasion-resistant coatings.

Dynasylan® SILBOND® Pure is immiscible with water, so hydrolysis requires the use of a co-solvent such as ethanol. Suitable catalysts are mineral acids or ammonia, or even acetic acid and amines.

Partial hydrolysis gives hydrolysates of Dynasylan® SILBOND® Pure whose shelf-life depends on the amount of water and solvent used. The amount of water determines the activity of the hydrolysate. Activity and shelf-life are inversely proportional. The correct choice for the amount of water can give hydrolysates, which have a shelf life of up to a year (from the time of manufacture).

Product Composition

Product Composition	Unit	Value
Silicon Dioxide (SiO₂) Content	wt%	28.0-30.0

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

Dynasylan® SILBOND® Pure is a clear, low-viscosity liquid that is essentially pure tetraethyl orthosilicate monomer (99.0%). Dynasylan® SILBOND® Pure is used as a building block for zeolites and catalyst carriers, crosslinking agent, chemical intermediate, clear-coat component, and in any other application requiring pure TEOS monomer.

HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://www.evonik.com/en/company/businesslines/se.html> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® SILBOND® Pure could be available in pails, drums, totes and tanker quantities.

Please ask for further details.

SHELF LIFE

In the unopened container Dynasylan® SILBOND® Pure has a shelf life of min. 24 months from date of manufacture.

Registration Listings

Registry	Status
Australia (AIIC)	Yes
Canada (DSL)	Yes
China (IECSC)	Yes
EU (REACH)	Yes
Japan (ENCS)	Yes
South Korea (KECL)	Yes
New Zealand (NZIoC)	Yes
Philippines (PICCS)	Yes
Taiwan (TCSI)	Yes
USA (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects