Technical Datasheet

INEOS Composites

AROPOL™ MR 13057 Resin

Description

This document provides typical properties, commercial warranty and storage conditions for Aropol MR 13057 resin.

Equivelant Products

Aropol MR 13057 Resin is identical to the discontinued product Laminac 4128 NP resin.

Typical Liquid Resin Properties

Property[1]	Value	Unit
Non-Volatiles Content	66	%
Viscosity, Brookfield RV #2 @ 20 rpm, cps	775	mPa·s (cps)
SPI Gel @180°F	4	minutes
Peak Exotherm Time	2	minutes
Peak Exotherm Temperature	430	°F
Catalyst: 2% ATC Paste		

[1] Properties are run at 25°C (77°F) unless otherwise stated. Properties are typical values, based on target values and not an analysis of any specific lot.

Certificates and Approvals

The manufacturing, quality control and distribution of products, by INEOS Composites, comply with one or more of the following programs or standards: ISO 9001, Responsible Care, ISO 14001 and OHSAS 18001.

Standard Package

Steel Drum with net weight of 220 KG (485 lb)

Commercial Warranty

Three months from date of shipment, when stored in accordance with the storage conditions stated below.

INEOS Composites is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.
® Registered trademark and ™ trademark INEOS Composites

Technical Datasheet

INEOS Composites

AROPOL™ MR 13057 Resin

Storage

Drums - Store at temperatures below 25°C (77°F). Storage life decreases with increasing storage temperature. Avoid exposure to heat such as direct sunlight or steam pipes. To avoid contamination of the product with water, do not store outdoors. Keep sealed to prevent moisture pick-up and monomer loss. Mild mixing is recommended after prolonged storage. Rotate stock.

Bulk - Refer to INEOS Composites's Bulk Storage and Handling Manual for Polyesters and Vinyl Esters. A copy of this may be obtained from INEOS Composites at 1-614-790-3333 or 1-800-523-6963.

All other conditions being equal, higher storage temperatures will reduce product stability and lower storage temperature will extend product stability.

Notice

All information presented herein is believed to be accurate and reliable, and is solely for the user's consideration, investigation and verification. The information is not to be taken as an express or implied representation or warranty for which INEOS Composites assumes legal responsibility. Any warranties, including warranties of merchantability, fitness for use or non-infringement of intellectual property rights of third parties, are herewith expressly excluded.

Since the user's product formulations, specific use applications and conditions of use are beyond the control of INEOS Composites, INEOS Composites makes no warranty or representation regarding the results which may be obtained by the user. It shall be the sole responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.

INEOS Composites requests that the user reads, understands and complies with the information contained herein and the current Material Safety Data Sheet.

More Information

INEOS Composites
5220 Blazer Parkway
Dublin, OH, 43017

Tel: +1 614 790 9299
Email: Americascustomer.composites @INEOS.com

INEOS Composites is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.
® Registered trademark and ™ trademark INEOS Composites