

# CERAFLOUR 967

Synthetic polymer for powder coatings to obtain coarse-textured surfaces. In conjunction with metal pigments, uniform hammertone and antique surfaces can be achieved.

## Product Data

### Composition

Synthetic polymer

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Particle size: < 1000 µm

Density: 1.11 g/cm<sup>3</sup>

Supplied as: Powder

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

## Applications

### Powder Coatings

#### Special Features and Benefits

The additive is used to obtain coarse-textured powder coating surfaces. It is very compatible and provides homogenous and highly reproducible textural effects. Adding metal pigments creates uniform hammertone and antique surfaces. Excellent separation of the metal pigments is achieved in this system.

#### Recommended Levels

0.1-0.3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

The additive is mixed with resin, hardener, pigments and other additives in a high-speed mixer and then extruded together with all components.

#### Special Note

The creation of texture with CERAFLOUR 967 is only possible when not using a leveling agent at the same time. When using leveling additives at the same time, a non-textured surface with craters is the result.

## CERAFLOUR 967

Data Sheet  
Issue 06/2017



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® **are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany