Texicryl® 13-064

Acrylic Dispersions

Technical Data Sheet

Product overview

TEXICRYL® 13-064 is a pure acrylic copolymer emulsion.

TEXICRYL® 13-064 has been developed as cement binder.

Characteristics (Not to be taken as a specification)	
Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	0.75 dPa.s
pH	8.5
Particle Size	160nm
Glass transition temperature	9°C

Application

TEXICRYL® 13-064 has been specially developed for cement application, and give to the mixture a better flexibility, resilience and good impact resistance.

TEXICRYL® 13-064 does not provide ammonia smell.

Packaging and storage

TEXICRYL 13-064 may be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-064 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

Health and safety

Please see separate material safety data sheet.

© 2021 Scott Bader Company Limited, March 2020, Issue No. 2

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

Scott Bader Company Limited
Wollaston, Wellingborough, Northants NN29 7RL
44 (0)1933 663738
enquiries@scottbader.com