

BYK-4500

Adhesion promoter for aqueous and solvent-borne and systems.

Product Data

Composition

Solution of modified alkylene copolymer

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value: 28 mg KOH/g

Density (20 °C): 1.00 g/ml

Solvents: 2,2,4-Trimethyl-1,3-pentanediol-monoisobutyrate

Flash point: 103 °C

Applications

Coatings Industry

Special Features and Benefits

The silicone-free additive is attracted by the coating interfaces and its effectiveness as an adhesion promoter is primarily due to special basic adhesion groups.






In aqueous systems, it improves adhesion, especially wet adhesion, on critical substrates, such as aged coatings, oxidized steel, galvanized steel, and polar plastics, such as ABS and glass-fiber reinforced polyester. Early water resistance is increased as well. Suitable systems are emulsion paints, alkyd emulsions, hybrid systems, and water reducible alkyd resin systems.

In solvent-borne systems (thermoplastic acrylates, epoxy resin ester, melamine resin cross-linking baking systems), adhesion on oxidized and galvanized steel is improved.

Hardness, flexibility, gloss, and yellowing tendencies of the coating are not negatively affected. In some cases, adhesion on subsequent coatings may be improved as well.

The additive is stable even at high baking temperatures (briefly up to 280 °C) and does not cause yellowing.

Recommended Use

Architectural coatings	
Industrial coatings	
Coil coatings (on galvanized steel)	
Protective coatings	
Automotive coatings	

 particularly recommended

Recommended Levels

1-3 % additive (as supplied) based upon total formulation.

The levels recommended above are purely for orientation purposes. Optimal dosage levels are determined through series of tests.

Incorporation and Processing Instructions

In solvent-borne systems, the additive is added to the letdown or the finished paint while stirring continuously. In aqueous systems, it is only added after the entire batch of binder and, if applicable, co-solvents in the formulation have been added.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.