

BYK-057

Silicone-free defoamer on polymer-basis for solvent-borne and solvent-free coatings and printing inks.

Product Data

Composition

Solution of polyolefin

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.89 g/ml
Non-volatile matter (10 min., 150 °C):	44 %
Solvents:	Solvent Naphtha/Methoxypropyl acetate 8/1
Flash point:	46 °C

Applications

Coatings Industry

Special Features and Benefits

BYK-057 is effective as a defoamer in unsaturated polyesters, acrylic/vinyl acetate combinations, epoxy resins, and oil-free polyesters. The additive furthermore acts as an air-releasing agent and improves leveling.

Recommended Use

Industrial coatings	<input checked="" type="checkbox"/>
Architectural coatings	<input type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>
Coil coatings	<input checked="" type="checkbox"/>
Protective coating systems	<input checked="" type="checkbox"/>

☒ particularly recommended ☐ recommended

Recommended Levels

0.1-1.5 % additive (as supplied) based upon total formulation.

The dosage levels are indicated for the purpose of orientation. Optimal dosage levels are determined through series of tests.

Incorporation and Processing Instructions

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated at a later time, sufficient shear forces must be ensured in order to achieve good defoamer distribution and to prevent crater formation.

Printing inks and overprint varnishes

Special Features and Benefits

BYK-057 prevents the formation of foam in printing inks and overprint varnishes during manufacture and application. It prevents the formation of foam and bubbles during processing. The additive has an immediate foam-destroying effect and does not reduce intercoat adhesion during recoating.

Applications

Particularly recommended for solvent-free UV curable printing inks and overprint varnishes.

Recommended Levels

0.1-1.5 % additive (as supplied) based upon total formulation.

The dosage levels are indicated for the purpose of orientation. Optimal dosage levels are determined through series of tests.

Incorporation and Processing Instructions

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated at a later time, sufficient shear forces must be ensured in order to achieve good defoamer distribution and to prevent crater formation.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.